



R.I.T.A CORPORATION Technical Data Sheet

RITA PEO-1
(INCI Nomenclature (formerly CTFA) PEG-5M)

DEFINITION: PEG-5M is the polymer of ethylene oxide hat conforms generally to the formula:



where n has an average value of 5000

DESCRIPTION: RITA PEO-1 is a water soluble, very mild, nonionic polymer compatible with most personal care ingredients. It adds lubricity to a formulation and has excellent film forming properties. Use concentration: 0.1-1%

GENERAL DATA:

Physical Form @ 25°F	White powder
App. Molecular Weight	210,000
Softening Point, °C	65-67
Bulk Density, g/cm ³	0.30
CAS Number	25322-68-3 (generic)

SPECIFICATIONS:

IR	TMS
Viscosity (5% w/w aqueous)(RV, #1, 12RPM)@25°C	50-200 cps
Loss on Drying, %	1.0 Max
Residue on Ignition	
Silicon Dioxide, %	3.0 Max
Non-Silicon Dioxide, %	2.0 Max
Heavy Metals, %	0.001 Max
Free Ethylene Oxide, %	0.001 Max
OVI	Complies with USP

RECEIVED
OCT 25 2000
101100 MAIL ROOM

The information contained herein is to our best knowledge true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. R.I.T.A CORPORATION disclaims any liability incurred in connection with the use of these data or suggestions.

PO Box 1487 ~ Woodstock, IL. 60098 USA
Tel: (815) 337-2500 ~ Fax: (815) 337-2522



Dated : 10/20/94
Updated: 12/15/95

R.I.T.A Corporation Technical Data Sheet

RITA PEO-2
(INCI Nomenclature (formerly CTFA) PEG-9M)

DEFINITION: PEG-9M is the polymer of ethylene oxide that conforms generally to the formula:



where n has an average value of 9000

DESCRIPTION: RITA PEO-2 is a water soluble, very mild, nonionic polymer compatible with most personal care ingredients. It adds lubricity to a formulation and has excellent film forming properties. Use concentration: 0.1-1%

GENERAL DATA:

Physical Form @ 25°F	White powder
App. Molecular Weight	400,000
Softening Point, °C	65-67
Bulk Density, g/cm ³	0.30
CAS Number	25322-68-3 (generic)

SPECIFICATIONS:

Viscosity (5% w/w aqueous)	200-2500 cps
pH (5% w/w aqueous)	6-8
Particle Size	<16 Mesh

RECEIVED
OCT 25 2008
TC 1700 MAIL ROOM

The information contained herein is to our best knowledge true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. R.I.T.A CORPORATION disclaims any liability incurred in connection with the use of these data or suggestions.

PO Box 1487 ~ Woodstock, IL. 60098 USA
Tel: (815) 337-2500 ~ Fax: (815) 337-2522



Dated: 10/20/94
Updated: 12/15/95

R.I.T.A Corporation Technical Data Sheet

RITA PEO-3
(INCI Nomenclature (formerly CTFA) PEG-23M)

DEFINITION: PEG-23M is the polymer of ethylene oxide that conforms generally to the formula:



where n has an average value of 23000

DESCRIPTION: RITA PEO-3 is a water soluble, very mild, nonionic polymer compatible with most personal care ingredients. It adds lubricity to a formulation and has excellent film forming properties. Use concentration: 0.1-1%

GENERAL DATA:

Physical Form @ 25°F	White powder
App. Molecular Weight	1,000,000
Softening Point, °C	65-67
Bulk Density, g/cm ³	0.30
CAS Number	25322-68-3 (generic)

SPECIFICATIONS:

Viscosity (5% w/w aqueous)	2500-5500 cps
pH (5% w/w aqueous)	6-8
Particle Size	<16 Mesh

RECEIVED
OCT 25 2000
TC 1700 MAIL ROOM

The information contained herein is to our best knowledge true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. R.I.T.A CORPORATION disclaims any liability incurred in connection with the use of these data or suggestions.

PO Box 1487 ~ Woodstock, IL. 60098 USA
Tel: (815) 337-2500 ~ Fax: (815) 337-2522



Dated: 10/20/94
Updated: 12/15/95

R.I.T.A Corporation Technical Data Sheet

RITA PEO-8
(INCI Nomenclature (formerly CTFA) PEG-45M)

DEFINITION: PEG-45M is the polymer of ethylene oxide that conforms generally to the formula:



where n has an average value of 45000

DESCRIPTION: RITA PEO-8 is a water soluble, very mild, nonionic polymer compatible with most personal care ingredients. It adds lubricity to a formulation and has excellent film forming properties. Use concentration: 0.1-1%

GENERAL DATA:

Physical Form @ 25°F	White powder
App. Molecular Weight	1,900,000
Softening Point, °C	65-67
Bulk Density, g/cm ³	0.30
CAS Number	25322-68-3 (generic)

SPECIFICATIONS:

Viscosity (0.5% w/w aqueous)	20-70 cps
pH (0.5% w/w aqueous)	6-8
Particle Size	<16 Mesh

RECEIVED
OCT 25 2000
TC 1700 MAIL ROOM

The information contained herein is to our best knowledge true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. R.I.T.A CORPORATION disclaims any liability incurred in connection with the use of these data or suggestions.

PO Box 1487 ~ Woodstock, IL. 60098 USA
Tel: (815) 337-2500 ~ Fax: (815) 337-2522



Dated: 10/20/94
Updated: 12/15/95

R.I.T.A Corporation Technical Data Sheet

RITA PEO-18
(INCI Nomenclature (formerly CTFA) PEG-90M)

DEFINITION: PEG-90M is the polymer of ethylene oxide that conforms generally to the formula:



where n has an average value of 90000

DESCRIPTION: RITA PEO-18 is a water soluble, very mild, nonionic polymer compatible with most personal care ingredients. It adds lubricity to a formulation and has excellent film forming properties. Use concentration: 0.1-1%

GENERAL DATA:

Physical Form @ 25°F	White powder
App. Molecular Weight	4,400,000
Softening Point, °C	65-67
Bulk Density, g/cm ³	0.30
CAS Number	25322-68-3 (generic)

SPECIFICATIONS:

Viscosity (0.5% w/w aqueous)	250-430 cps
pH (0.5% w/w aqueous)	6-8
Particle Size	<16 Mesh

RECEIVED
OCT 25 2000
TC 1700 MAIL ROOM

The information contained herein is to our best knowledge true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. R.I.T.A CORPORATION disclaims any liability incurred in connection with the use of these data or suggestions.

PO Box 1487 ~ Woodstock, IL. 60098 USA
Tel: (815) 337-2500 ~ Fax: (815) 337-2522



Dated: 10/20/94
Updated: 12/15/95

R.I.T.A Corporation Technical Data Sheet

RITA PEO-27
(Tentative INCI Nomenclature (formerly CTFA) PEG-160M)

DEFINITION: PEG-160M is the polymer of ethylene oxide that conforms generally to the formula:



where n has an average value of 160000

DESCRIPTION: RITA PEO-27 is a water soluble, very mild, nonionic polymer compatible with most personal care ingredients. It adds lubricity to a formulation and has excellent film forming properties. Use concentration: 0.1-1%

GENERAL DATA:

Physical Form @ 25°F	White powder
App. Molecular Weight	7,200,000
Softening Point, °C	65-67
Bulk Density, g/cm ³	0.30
CAS Number	25322-68-3 (generic)

SPECIFICATIONS:

Viscosity (0.5% w/w aqueous)	600-800 cps
pH (0.5% w/w aqueous)	6-8
Particle Size	<16 Mesh

RECEIVED
OCT 25 2000
TC-1700 MAIL ROOM

The information contained herein is to our best knowledge true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. R.I.T.A CORPORATION disclaims any liability incurred in connection with the use of these data or suggestions.

PO Box 1487 ~ Woodstock, IL. 60098 USA
Tel: (815) 337-2500 ~ Fax: (815) 337-2522